



DynaGuard™ Hydrophobic Tape Microporous Insulation

DynaGuard™ Hydrophobic Tape- Insulation Systems

DynaGuard™ Hydrophobic insulation Systems represent one of Thermo Dyne's microporous products for primary use in industrial and commercial applications. The DynaGuard Tape system is a flexible, textile encased, comparatively dense material with high compression resistance and exceptional strength, and its superior thermal performance allows the maximum amount of thermal protection to be provided within minimum space and weight requirements.

DynaGuard™ Hydrophobic Tapes are also specially formulated to minimize heat transfer via conduction, convection and radiation through the material by use of the following:

Ceramic Powders with Intrinsically Low Thermal Conductivity

The microporous core materials used in the manufacture of DynaGuard™ Hydrophobic tape possess a thermal conductivity even lower than that of still air, and minimize the solid conduction of energy through the material.

Microporous Structure

The microporous structure of the DynaGuard™ Tape system inherently minimizes the possibility for air current convection through the material as void spaces too small for air currents to exist form between the core material components.

Special Opacifiers

The introduction of special opacifiers into the DynaGuard™ Tape formulation ensures that the transmission of infrared radiation through the material is kept to the lowest possible levels.

DynaGuard™ Hydrophobic Tape- Materials of Construction

The DynaGuard™ Hydro Tape microporous core material is an 1,800°F continuous use formulation, and is compressed into a uniform thickness and density to ensure the proper distribution of the core material. After compression, the material is wrapped with high temperature fiberglass fabric in order to provide both flexibility and greater vibration resistance for the material.

Unlike other DynaGuard™ products, DynaGuard™ Hydro Tape also possesses a hydrophobic component in its core formulation. This material makes the microporous structure highly resistant to the presence of moisture during

use and installation, and is capable of performing at temperatures as high as 900°F before burning out of the microporous formulation.

DynaGuard™ Tape systems are supplied standard at 14 lbs/ft³ density, 2", 3", 6", and special widths. Thickness 1/8" to 1/4", and with a fiberglass textile shell (1,000°F use limit). Other densities, sizes, thicknesses and cloth facings are Available on request.

DynaGuard™ Hydrophobic Tape- Insulation Systems Advantages Lowest Thermal Conductivity

Because DynaGuard™ Hydro Tape systems inherently possess a thermal conductivity lower than that of still air, even at elevated temperatures, they are ideal in environments where materials with low thermal conductivity, thermal diffusivity and heat storage are necessary.

Space and Weight Savings

Because smaller amounts of DynaGuard™ Hydro Tape are needed for thermal management, it is an ideal material for industrial and commercial applications where considerable space and/or weight savings are valuable in increasing capacity or efficiency without sacrificing the thermal performance of the system.

High Temperature Capability

DynaGuard™ Hydro Tape systems can be manufactured to meet continuous high temperature environments up to 1,800°F, but are also capable of performing in intermittent exposure to 2,000°F temperatures.

Easy Fabrication

Shapes can be covered in the field by various wrapping methods, but Thermo Dyne also provides a virtually limitless range of custom pre-fabricated and intricate shapes upon request.

Thermal Conductivity Data (Btu - in/hr - ft² - °F)*

DynaGuard™ Hydrophobic Tape 14 lbs/ft

Mean Temp. °F (°C)	Thermal Conductivity
0°F (-17°C)	0.097 (.014 W(m·K))
500°F (260°C)	0.104 (.015 W(m·K))
1,000°F (538°C)	0.118 (.017 W(m·K))
1,500°F (816°C)	0.201 (.029 W(m·K))

*NOTE: All thermal conductivity values have been measured in accordance with ASTM Test Procedure C-177. When comparing similar data, it is advisable to check the validity of all thermal conductivity values and ensure the resulting heat flow calculations are based on the same condition factors. Variations in any of these factors will result in significant differences in the calculated data.

Typical Characteristics

Core Density 14 lbs/ft³ (225kg/m³) Standard

Widths 2", 3", 6" or special

Thickness 1/8", 3/16", 1/4"

NOTE: Other non-standard sizes are available in many thicknesses and densities.

Application Comparison Example

Material	DynaGuard™ Ladle Liner 14 lbs/ft ³	Ceramic Fiber Blanket 8 lbs/ft ³
Thickness	1" (24.5mm)	1" (24.5mm)
Ambient	80°F (26.7°C)	80°F (26.7°C)
Convection	Natural	Natural
Hot Face	1,800°F (982°C)	1,800°F (982°C)
Resultant Cold Face	281°F (138°C)	470°F (243°C)
Heat Flux	484 Btu/hr/ft ² /°F	1,335 Btu/hr/ft ² /°F

NOTE: Figures are based on computer simulations using thermal performance calculations conforming to ASTM C-680, and should be used for comparisons and approximation rather than for exact design specifications.

For technical and installation support for DynaGuard™ Microporous Insulation, please contact ThermoDyne's application engineering team.

Approximate Energy Savings Comparison

The two materials used in the above example have the following differences in temperature and heat flux:

Difference in Cold Face Temperature = 189°F (87°C)

Difference in Heat Flux = 851 Btu/hr/ft²/°F

Result = DynaGuard™ Ladle Liner saves approximately \$.016/kilowatt hr/ft² over Ceramic Fiber Blanket of equal thickness.

NOTE: Assumes 1kWh = 3,413 Btu, \$.065/kWh estimated energy cost.



DynaGuard™ Space Savings

A 3" layered thickness (66% more material) of 8 lbs/ft³ Ceramic Fiber Blanket is necessary to achieve equal thermal performance of 1" DynaGuard™ Ladle Liner 14 lbs/ft³.

DynaGuard™ Weight Savings

Amount of weight saved by using 1" of DynaGuard™ Ladle Liner 14 lbs/ft³ as opposed to 3" of 8 lbs/ft³ Ceramic Fiber Blanket = .7 lbs/ft².

DynaGuard™ Compression Data For 14 lbs/ft³



DynaGuard™ products offer a variety of solutions.

Industrial
 Power plant pipes, ducts
 Under ground pipes
 Molten metal ladle backup
 Glass tank forehearth
 Fuel cells

Commercial
 Lab furnaces
 Gas boilers
 Appliances
 Night storage heaters
 Vending machines
 Exhaust systems



Thermo Dyne

822 Middlebury St., Elkhart, IN 46516

Toll Free: 866.741.5458, 574.522.3606, Fax: 574.293.0047

www.ThermoDyne1.com

Form E-1008, Effective 10/09, ©2009, Thermo Dyne Corporation, All Rights Reserved, Printed in USA

The information, recommendations, and opinions set forth herein are offered solely for your consideration, inquiry and verification and are not, in part or total, to be construed as constituting a warranty or representation for which we assume legal responsibility. Nothing contained herein is to be interpreted as authorization to practice a patented invention without a license. The following is a registered trademark of Thermo Dyne Corporation: DynaGuard.